



# PRODUCT SPECIFICATION

## ORYKTO

2465 BOUL. FORD  
CHÂTEAUGUAY QC J6J 4Z2, CANADA

+1-438-497-8089 | [INFO@ORYKTO.CA](mailto:INFO@ORYKTO.CA)  
[WWW.ORYKTO.CA](http://WWW.ORYKTO.CA)

## OKOUMÉ WBP PLYWOOD

This **WBP** is the ideal solution for projects requiring enhanced **moisture resistance** without the weight of traditional plywood. Crafted with superior adhesives, this **100% OKOUME** plywood is ideal for CNC cutting.

### SIZES

#### DIMENSIONS

2440 MM X 1220 MM (4'X8')

#### THICKNESS/PLY

12 MM	15 MM	18 MM
-------	-------	-------



TECHNICAL PROPERTIES	STANDARD	UNIT	VALUE
Density	-	Kg/m <sup>3</sup>	530 to 560 ± 10%
WBP	EN 314	—	Can withstand minimum of 72 hours in boiling water
Glue Average Shear Strength	EN 314	N/mm <sup>2</sup>	1.59 - 1.72 N/mm <sup>2</sup>
Bending Strength: Long Grain / Cross Grain	EN 310	N/mm <sup>2</sup>	37.1 - 69.7 N/mm <sup>2</sup>
Modulus of Elasticity Along the Grain	EN 310	N/mm <sup>2</sup>	7.390 N/mm <sup>2</sup>
Modulus of Elasticity Across the Grain	EN 310	N/mm <sup>2</sup>	4.230 N/mm <sup>2</sup>